

Coherent NuUF Ultrafast Fibers



Coherent NuUF fibers offer customers an opportunity to scale up power while avoiding the costs and risks associated with solid state designs. Our fibers provide a path to a seamless transition to a higher powered system with significantly reduced \$/W.

Our PM, large mode area (PLMA) Ytterbium doped active fibers (YDF) and passive matched Germanium doped Fibers (GDF) are tailored to meet key requirements for ultrafast laser designs. These specialty fibers feature polarization maintenance, dispersion control, high beam quality, low photodarkening, and highest absorption.

These fibers are also highly suitable for other applications that are sensitive to nonlinear effects including narrow linewidth amplification, second harmonic generation, frequency doubling, and short pulse amplification.

Typical Applications

- Ultrafast Fiber Lasers for Material Processing
 - Chirped Pulse Amplification
 - Second Harmonic Generation
 - Frequency Doubling
 - Single Frequency & Narrow Linewidth Amplifiers

Features & Benefits

- Lowest Photodarkening – increased reliability and enables power scaling of pulsed amplifiers
- Highest Absorption – 2-3x absorption reduces cavity length and minimizes nonlinear effects
- Maintains highest beam quality
- Enables power scaling and mass production
- Reduces \$/w
- Designed for extended service life in challenging deployment conditions

Optical Specifications

Operating Wavelength
Core NA
First Cladding NA (5%)
Core Attenuation

PLMA-YDF-14/125-UF

1015 – 1115 nm
0.07 ± 0.005
≥ 0.46
≤ 25.0 dB/km @ 1200 nm

PLMA-YDF-25/250-UF

1015 – 1115 nm
0.07 ± 0.005
≥ 0.46
≤ 25.0 dB/km @ 1200 nm

PLMA-YDF-30/250-UF

1015 – 1115 nm
0.07 ± 0.005
≥ 0.46
≤ 25.0 dB/km @ 1200 nm

Cladding Attenuation
Cladding Absorption

≤ 15.0 dB/km @ 1095 nm
3.9 ± 0.5 dB/m at 915 nm
16.6 dB/m near 976 nm

≤ 15.0 dB/km @ 1095 nm
2.8 ± 0.3 dB/m at 915 nm
11.9 dB/m near 976 nm

≤ 15.0 dB/km @ 1095 nm
4 ± 0.6 dB/m at 915 nm
17 dB/m near 976 nm

Birefringence

nominal 2×10^{-4}

nominal 2×10^{-4}

nominal 2×10^{-4}

Geometrical & Mechanical Specifications

Cladding Diameter
Cladding Diameter (flat-to-flat)
Core Diameter
Coating Diameter
Core/Clad Offset
Proof Test Level

125.0 ± 1.0 μm
N/A
14.0 ± 1.0 μm
245.0 ± 10.0 μm
≤ 1.00 μm
≥ 100 kpsi (0.7 GN/m²)

255.0 ± 5.0 μm
N/A
25.0 ± 1.5 μm
395.0 ± 15.0 μm
≤ 2.00 μm
≥ 100 kpsi (0.7 GN/m²)

255.0 ± 5.0 μm
N/A
30.0 ± 2.5 μm
395.0 ± 15.0 μm
≤ 2.00 μm
≥ 100 kpsi (0.7 GN/m²)

Precision matched NuUF passive fibers are also available - PLMA-GDF-14/125-UF; PLMA-GDF-25/250-UF; PLMA-GDF-30/250-UF



Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.