



FUD-4239, Revision: A PLMA-YDF-10/125-HA Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	1060		1115	nm	Design
Cladding Attenuation at 1095nm	0		15	dB/km	Measured
Peak Cladding Absorption at 915 nm	1.9		2.3	dB/m	Measured
Peak Cladding Absorption near 976 nm		6		dB/m	Design
Core NA		0.082			Design
Cladding NA (5%)	0.46				Design
Cutoff	900		1050	nm	Measured
Mode Field Diameter at 1080 nm	9.7		11.7	μm	Measured
Birefringence		0.0003			Design
Core Diameter		10		μm	Design
Clad Diameter	123		127	μm	Measured
Core/Clad Offset	0		1	μm	Measured
Coating Diameter	230		260	μm	Measured
Proof test Level	100		120	kpsi	Measured
Comments	Coating Requirements: Low Index polymer coating.				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.