



FUD-4279, Revision: A MM-S200/220-22S Optical Fiber

You have selected an application designed fiber, not fully released which may have a longer lead time than our standard products.

Parameter	Min	Nom	Max	Unit	Compliance
Operating Wavelength	800		1600	nm	Design
Core NA	0.2	0.22	0.24		Measured
Core Diameter	196		204	μm	Measured
Clad Diameter	217		223	μm	Measured
Core/Clad Offset	0		5	μm	Measured
Coating Diameter	315		345	μm	Measured
Proof test Level	100		120	kpsi	Measured
Customer comment:	Radius bend method.				
Comments	Low or High -OH Core: Low Coating Requirements: Thermally cured silicone.				



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com •
Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.