

# 10/200 NuGEN9 Precision Matched Active LMA Double Clad Fiber

NuGEN9 active fibers offer the most advanced glass composition and fiber design and are all precision matched to their passive counterpart ensuring excellent splice compatibility and low loss. This fiber is a Yb-doped Large Mode Area (LMA) active double clad fiber featuring a 10 micron diameter core and 200 micron clad diameter with a low NA (0.08) core. This fiber is ideally suited for applications spanning military, industrial and medical applications. NuGEN9 fibers feature an optimized glass composition enabling higher absorption with superior photodarkening performance. These fibers are prooftested to 100 kpsi, an industry requirement for long term reliability. NuGEN9 fibers are exclusively offered with Coherent's proprietary NuCOAT-FA coating technology with the best wet and dry heat performance available, ensuring excellent preservation of beam quality and extended operating life.

#### **Typical Applications**

- Pulsed fiber lasers and amplifiers
- · Material processing
- LIDAR
- Non-linear optics/frequency doubling

## **Features & Benefits**

- NuGEN9 fiber design Providing higher absorption with superior reliability & photodarkening performance
- NuCOAT-FA fluoroacrylate coating Excellent wet and dry heat performance for extended life in extreme conditions LMA core design and short amplifier length — Useful for generating high peak powers
- "Few" moded core design Easy to maintain single mode LP01 beam through fiber & components
- All fiber proof tested to > 100 kpsi Critical for ensuring long term reliability when coiling

#### **Optical Specifications**

Operating Wavelength
Core NA
First Cladding NA (5%)
Cladding Attenuation
Cladding Absorption

## Geometrical & Mechanical Specifications

Cladding Diameter (flat-to-flat)
Core Diameter
Coating Diameter
Core/Clad Offset
Coating Material
Prooftest Level

# LMA-YDF-10/200-9M

1015 - 1115 nm  $0.080 \pm 0.005$ ≥ 0.46 ≤ 15.0 dB/km @ 1095 nm  $0.60 \pm 0.10 \text{ dB/m at } 915 \text{ nm}$ 

 $205.0 \pm 4.0 \ \mu m$   $10.0 \pm 1.0 \ \mu m$   $350.0 \pm 10.0 \ \mu m$   $\leq 1.20 \ \mu m$ Low Index Acrylate  $\geq 100 \ kpsi \ (0.7 \ GN/m^2)$ 



The precision matched passive version of this fiber is also available - see LMA-GDF-10/200-M



