



25/250 Precision Matched Passive LMA Double Clad Fibers

Coherent's Large Mode Area (LMA) and Polarization Maintaining LMA (PLMA) passive double clad fiber are ideal for high power fiber lasers and amplifiers used in military, industrial, and medical applications. These fibers feature a 25 micron diameter core and 250 micron diameter clad size with a low NA (0.065) core. They are precision matched to their active Yb-doped 25/250 LMA and PLMA matched counterparts to ensure excellent splice compatibility and low loss. As with all Coherent standard Large Mode Area (LMA) fibers, these fibers are proof-tested to 100 kpsi, an industry requirement for long term reliability. They utilize the latest fiber design and NuCOAT™ coating technology to ensure excellent preservation of beam quality and extended operating life at the high power levels demanded by today's industrial fiber laser applications. These precision matched fibers are available in both non-PM and PANDA-style PM fibers.

Typical Applications

- High peak power amplifiers
- LIDAR
- Material processing
- Non-linear optics/frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design and short amplifier length — Useful for transmitting high peak powers
- “Few” moded core design — Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence — Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

Operating Wavelength
Core NA
First Cladding NA (5%)
Core Attenuation
Cladding Attenuation
Birefringence

PLMA-GDF-25/250-M

1060 – 1600 nm
0.065 ± 0.005
≥ 0.46
≤ 45.0 dB/km @ 1300 nm
≤ 30.0 dB/km @ 1200 nm
≤ 15.0 dB/km @ 1095 nm
nominal 2×10^{-4}

LMA-GDF-25/250-M

1060 – 1600 nm
0.065 ± 0.005
≥ 0.46
≤ 45.0 dB/km @ 1300 nm
≤ 30.0 dB/km @ 1200 nm
≤ 15.0 dB/km @ 1095 nm
N/A

Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Core/Clad Offset
Clad Non-Circularity
Proof-test Level

247.0 ± 5.0 μm	247.0 ± 3.0 μm
25.0 ± 1.5 μm	25.0 ± 1.5 μm
395.0 ± 15.0 μm	395.0 ± 15.0 μm
≤ 2.00 μm	≤ 2.00 μm
N/A	≤ 0.5 %
≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)



These precision matched fibers are included in our precision matched sets - see PLMA-YDF-25/250-M and LMA YDF-25/250-M

Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.

NU0155- 11/12/2020