

Polarization Maintaining 14XX nm Telecommunication Fibers



Coherent's Polarization Maintaining Telco fibers are designed for today's most advanced networks. Optimized for use in the 1400-1500 nm range, these fibers are used in all PM applications for data and telecom. Coherent has applied its unique manufacturing facility and capabilities to this product area and has established leading optical, mechanical and geometrical tolerances. The bend insensitive versions of our fibers offer lowest bend loss and extinction ratios at small bend diameters enabling our customers to reduce package sizes. Available in either 250 or 400 micron coating diameters and prooftested to 200 kpsi, Coherent's PM fibers will meet the demands of all current and future applications.

Typical Applications

- Pump pigtails
- Raman amplifiers
- PM patchcords
- Polarization sensitive devices

Features & Benefits

- Tight specifications — Highly deterministic results, highest product yield
- High fatigue failure resistance — Longest service life
- Bend insensitive — Survives application in tight geometries (B version)
- All fiber proof tested to > 200 kpsi — Critical for ensuring long term reliability

Optical Specifications

	PM14XX-XP	PM14XXB-XP	PM14XX-400	PM14XXB-400
Operating Wavelength	1380 – 1625 nm	1380 – 1625 nm	1380 – 1625 nm	1380 – 1625 nm
Core NA	0.125	0.125	0.125	0.125
Mode Field Diameter	9.5 ± 0.5 μm @ 1450 nm 9.9 ± 0.5 μm @ 1550 nm	9.5 ± 0.5 μm @ 1450 nm 9.9 ± 0.5 μm @ 1550 nm	9.5 ± 0.5 μm @ 1450 nm 9.9 ± 0.5 μm @ 1550 nm	9.5 ± 0.5 μm @ 1450 nm 9.9 ± 0.5 μm @ 1550 nm
Maximum Bend Loss	N/A	0.5 dB at 1550 nm, 25 mm OD, 10 turns	N/A	0.5 dB at 1550 nm, 25 mm OD, 10 turns
Cutoff	1320 ± 60 nm	1320 ± 60 nm	1320 ± 60 nm	1320 ± 60 nm
Core Attenuation	≤ 1.0 dB/km @ 1450 nm ≤ 1.0 dB/km @ 1550 nm	≤ 1.0 dB/km @ 1450 nm ≤ 1.0 dB/km @ 1550 nm	≤ 1.0 dB/km @ 1450 nm ≤ 1.0 dB/km @ 1550 nm	≤ 1.0 dB/km @ 1450 nm ≤ 1.0 dB/km @ 1550 nm
Beat Length	≤ 4.7 mm @ 1450 nm	≤ 4.7 mm @ 1450 nm	≤ 4.7 mm @ 1450 nm	≤ 4.7 mm @ 1450 nm
Normalized Cross Talk	≤ - 40.0 dB at 4 m @ 1550 nm ≤ - 30.0 dB at 100 m @ 1550 nm	≤ - 40.0 dB at 4 m @ 1550 nm ≤ - 30.0 dB at 100 m @ 1550 nm	≤ - 40.0 dB at 4 m @ 1550 nm ≤ - 30.0 dB at 100 m @ 1550 nm	≤ - 40.0 dB at 4 m @ 1550 nm ≤ - 30.0 dB at 100 m @ 1550 nm
Bending Cross Talk	N/A	-30 dB at 1550 nm, 25 mm OD, 10 turns	N/A	-30 dB at 1550 nm, 25 mm OD, 10 turns

Geometrical & Mechanical Specifications

Cladding Diameter	125.0 ± 1.0 μm	125.0 ± 1.0 μm	125.0 ± 1.0 μm	125.0 ± 1.0 μm
Core Diameter	8.0 μm	8.0 μm	8.0 μm	8.0 μm
Coating Diameter	245.0 ± 15.0 μm	245.0 ± 15.0 μm	400.0 ± 15.0 μm	400.0 ± 15.0 μm
Coating Concentricity	< 5.0 μm	< 5.0 μm	< 10.0 μm	< 10.0 μm
Core/Clad Offset	≤ 0.50 μm	≤ 0.50 μm	≤ 0.50 μm	≤ 0.50 μm
Coating Material	Acrylate	Acrylate	Acrylate	Acrylate
Operating Temperature Range	-40 to 85 °C	-40 to 85 °C	-40 to 85 °C	-40 to 85 °C
Prooftest Level	≥ 200 kpsi (1.4 GN/m ²)	≥ 200 kpsi (1.4 GN/m ²)	≥ 200 kpsi (1.4 GN/m ²)	≥ 200 kpsi (1.4 GN/m ²)



Special Core Dopants: SiO₂/GeO₂.

Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.

NU0139- 11/12/2020